MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD

DEVELOPMENT OF LARGE AREA MULTI-LAYER LIQUID PHASE EPITAXY FOR LARGE OPTICAL CAVITY LASER STRUCTURES

Robert B. Gill

Laser Diode Laboratories, Inc.

A Subsidiary of United Corp.

205 Forrest Street

Metuchen, New Jersey 08840

Final Technical Report.

Sep 74

52p.

U. S. Army Mobility Equipment

Research and Development Center

Night Vision Laboratory, USAECOM

Contract No. DAAK02-73-C-0254

Fort Belvoir, Virginia 22060

DDC

RECEIVED

DEC   1976

A

1473

dn

405626

FOREWARD

This Final Technical Report covers
the work performed under Contract No.
DAAK02-73-C-0254 between the period March
30, 1973 thru July 31, 1974.

This contract with Laser Diode Labs.,
was to fabricate by liquid phase epitaxy,
large optical cavity GaAs laser structures
having a minimum area of two (2) square
centimeters of usable material. Program
technical direction was provided by Mr.
Richard R. Schurtz, Night Vision
Laboratory, Fort Belvoir, Virginia. The
work was performed at Laser Diode
Laboratories, Metuchen, New Jersey under
the direction of R. B. Gill.

i

ABSTRACT

The development of a liquid phase eptixaial process
capable of yielding GaAlAs-GaAs multiple layer structures
from which efficient lasers can be fabricated is discussed.
The furnace facility is described in detail and the develop-
ment of the LPE process is described. The application of
various LPE processes to the growth of both large optical
cavity and symmetrical optical cavity lasers is presented.
Data is shown which depicts performance characteristics and
emission patterns for the resultant devices.

ii

TABLE OF CONTENTS

iii

LIST OF ILLUSTRATIONS

LIST OF TABLES

SECTION I

OBJECTIVE

The objective of this program is to fabricate, by liquid phase epitaxy, large optical cavity laser structures having a minimum cross-sectional area of two square centimeters and to demonstrate the quality of these structures by the characterization of injection lasers constructed from these wafers. To accomplish this objective the technical effort was divided into several parallel programs:

A. **Laser Structure Specification.** To identify the multiheterojunction laser configuration required for the fabrication of injection lasers meeting the technical requirements described under DAAK02-73-C-0254 dated 30 March, 1973.

B. **Liquid Phase Epitaxial Technology.** To develop a liquid phase epitaxial facility and epitaxial process required for the growth of large optical cavity laser structures.

C. **Device Evaluation.** To continuously evaluate laser diodes fabricated from the epitaxial layers and to correlate the lasing characteristics of these diodes to the laser structure and growth conditions.

SECTION II

RESULTS AND DISCUSSION

A.   General Requirements

The overall objective of this program was to
fabricate, by liquid phase epitaxy, large optical cavity
injection laser structures having a minimum cross-sectional
area of two square centimeters and to demonstrate the quality
and uniformity of these epitaxial wafers by the characterization
of injection lasers constructed from these wafers. The objective
performance characteristics of the injection lasers are
summarized in Table 1. Two types of laser structures were
investigated during this program to achieve the desired device
performance. Initially laser diodes which utilized the
multi-heterojunction laser cavity structure described by
Lockwood et al' in 1970 were fabricated. An outline of
this type of laser structure is shown schematically in Fig.
1. The structure itself is formed in a single thermal
cycle by sequential growth of layers of GaAlAs and GaAs onto
(100) single crystal GaAs substrate by liquid phase epitaxy.
The first grown layer (1) is n-type GaAs which serves as an
interface between the following (GaAl)As layer (2) and the
substrate material. While this first layer is not necessary
to the active laser structure, it generally absorbs submicron
nonuniformities in the first growth interface and provided a
uniform flat interface for the growth of the following layer.

"CROSS—SECTION OF GaAs LOC LASER"

Fig. 1. Schematic representation of GaAs LOC Laser

Layer 2 consists of n-type (GaAl)As doped with either Te or Sn and serves to confine the stimulated radiation and lasing mode to the optical waveguide D_c through its heterojunction interface with layer 3.

Layer 3, which forms the bulk of the waveguide region, consists of either lightly doped or undoped n-type GaAs. Its thickness (D_c-D) strongly effects the laser threshold current density, the primary propagating mode order, the emitted optical beam pattern and catastrophic damage level, while its free electron concentration effects both the lasing threshold and quantum efficiency. Layer 5 consists of P-type (GaAl)As whose interface with Layer 4 serves both as an optical barrier to confine the radiation and lasing mode to the waveguide region and as a potential barrier to confine the electrons injected from layer 3 into layer 4 within layer 4 where the radiative recombination occurs.

Finally, layer 6, consisting of p-type GaAs is grown to facilitate ohmic contacting to the P side of the structure. While not essential to the structure it does provide a surface that can be contacted relatively easily if a thin (GaAl)As layer is desired for layer 5.

As a general rule, for this structure, the energy gaps and refractive indices of the layers have the following relationship:

$$Eg_1 \simeq Eg_3 \simeq Eg_4 \simeq Eg_6 \simeq Eg_{sub}$$

$$n_1 \simeq n_3 \simeq n_4 \simeq n_6 \simeq n_{sub}$$

$$Eg_5 > Eg_2 > Eg_3$$

$$n_5 < n_2 < n_3 \quad \text{and}$$

for an asymmetrical LOC laser:

$$\frac{n_4 - n_5}{n_3 - n_2} \simeq \frac{n_3 - n_5}{n_3 - n_2} > 3$$

After considerable effort directed toward optimizing
the epitaxial process required for the generation of the
large optical cavity laser a parallel effort was established
toward evaluation of a laser structure in which the injected
carriers and optical wave would be separately confined.

This structure which is schematically represented in Figure
2 was first demonstrated by Panish[2] at Bell Telephone
Laboratories in 1973. In this structure the injected carriers
are confined to the p-type GaAs (region 3) by the hetero-
junctions located at its interface with the P and N type
GaAlAs layers. On the other hand the optical wave is confined
by the $GaAl_{1-x}As_x$ - $GaAl_{1-y}As_y$ heterojunctions which defines then a
heterostructural optical cavity consisting of regions 3,4 & 5.

CROSS SECTION OF GaAs SOC LASER.

D_R D_C

N E_0

7 6 5 4 3 2 1

P - GaAs
P - (Ga$_{1-Y}$AL)$_Y$As
P - (Ga$_{1-X}$AL$_X$)As
N - (Ga$_{1-X}$AL$_X$)As
N - (Ga$_{1-Y}$AL$_Y$)As
N - GaAs
N - GaAs SUBSTRATE

Figure 2. Schematic presentation of a GaAs Symmetrical Optical Cavity
Laser Diode

TABLE I

OBJECTIVE PERFORMANCE CHARACTERISTICS OF LOC GaAs INJECTION LASERS AT 27°C

Threshold Current Density	$7KAcm^{-2}$ (Max.)
Differential Quantrum Efficiency	35%
Emission Wavelength	$8950 \pm 50 \overset{\circ}{A}$
Peak Power Output A 200ns pulse width and 2KHz	1.5 watts/mil of laser facet **
Beam Spread, full angle at 10% points	35°

** Without use of an antireflective coating

This configuration results in a symmetrical optical cavity (SOC) GaAs laser structure. Results on devices of this type as reported by Panish[2] indicated the possibility to fabricate high power lasers operating in the first order transverse mode with lasing threshold current densities less than 5KAcm^{-2} at 27°C.

B.   **Materials Technology**

    1.   **Substrate Requirements**

        The **GaAlAs-GaAs multi-heterojunction laser**
structure required for both LOC and SOC injection
lasers is formed by multiple liquid phase epitaxial
growth onto GaAs substrates. All of the substrate
wafers used in this program were selected from high
quanlity GaAs single crystal ingots grown at LDL by
the horizontal gradient freeze technique. These
substrates were typically n-type with a net donor
concentration lying between 1.5 and 2.5 X $10^{18}cm^{-3}$,
contained dislocation densities less than $1500cm^{-2}$
and were doped with either Te, Sn or Si. Surface
orientation was maintained at 100 $\pm$ 0.3 degrees to
minimize growth defects due to misorientation. All
wafers were polished prior to growth using standard
commercial techniques.

2.   Liquid Phase Epitaxy

a.   Furnace Design

The multi-layer GaAlAs-Gaas structures required
for the fabrication of either LOC or SOC GaAs
injection lasers are generated by the growth of the
structure by liquid phase epitaxy onto GaAs
substrate in a single growth operation using a
multiple melt epitaxial boat. Since best results
are obtained when horizontal thermal gradients
across the boat are minimized, the epitaxial furnace
must have a long flat zone which can be programmed
to change uniformily at rates ranging from 0.1°C to 2°C
per minute at about 850°C. Since most commercial
furnaces which meet this requirement are both large
and complex, (multiple zone), a special roller
mounted furnace system utilizing a heat pipe core
was designed and constructed. The major elements
of the growth system developed under this contract
were patterned after a system already in use at the
Night Vision Laboratory, which included a heat pipe
core furnace, a Vac-Sorb pump and check valve
evacuation system, a slow cool temperature regulation
equipment, and a single end supported growth chamber
to allow furnace removal for fact cycling.   This
furnace system which was used throughout the program
is shown in Figure 3.

The furnace chamber which is critical to uniform
epitaxy was constructed at LDL. The furnace core
consists of #12 Kanthal A-L wire wound onto a 24

Figure 3.   Furnace system used for multi-layer liquid phase epitaxy.

Page 11

inch long by 2.5 inch bore Dynathern Isothermal
Furnace liner. Electrical isolation between the
heater element and the metallic core was achieved
by using eight 1/4 inch diameter alumina thermo-
couple sleeves mounted to the outside diameter of
the core as insulating stand-offs between the core
and the winding. After winding, the furnace core
was insulated with one layer of 100 series zircar
felt. This element was then mounted into a Marshall
clam shell furnace frame which had been stripped of
its original heater element and insulation. Three
shaped firebricks were used to position the furnace
core at the center of the clam shell enclosure.
The entire enclosure was then packed with fiber frax
to reduce heat loss. With the furnace growth tube
inserted into the core and a heat reflector positioned
at one end of the core this chamber provides a thermal
flat zone at 900°C)$\pm$ 0.2°C) of at least 20 inches.

Temperature controlled during epitaxy is
provided by a continuously programmable furnace
power supply. Using a modified Data Trak Controller-
programmer combination, a full scale programmable
interval of 15°C lying between 800°C and 900°C can
be selected for epitaxy.

Initially two platinum-platinum plus 13% rhodium thermocouples were used to control and sense furnace temperature. One was placed within the furnace core and the second within the quartz growth tube. When the furnace was in the standby position the furnace thermocouple was used to maintain the furnace core at 850°C, when the growth tube with the epitaxial boat positioned within it was inserted into the furnace, furnace thermal monitoring and control was switched to the second thermocouple which was mounted within the tube. This set up proved to be unsatisfactory due to frequent damage to the tube thermocouple during growth and lack of thermal reproducibility and stability. The dual thermocouple arrangements was replaced by a single thermocouple mounted on the isothermal furnace liner wall. Results with this system have been very satisfactory with current re-producibility estimated to be approximately 0.3°C at 850°C and stability better than 0.1°C.

The epitaxial growth chamber consists of a quartz tube secured with an "O" ring seal to the stainless steel furnace head. Initially viton

"O" rings were used but these proved unsatisfactory after a number of growth cycles. Currently silicone "O: rings are used at the glass to metal seal.

The furnace head contains the ambient gas input and exhaust lines, a thermocouple guage for monitoring system gas pressure and a vacuum line for exhausting the system during pre-growth purging. The furnace head is sealed at the loading end with a stainless steel flange which contains the quartz push rod used to propel the epitaxial boat slide and cause transport of the wafer from one bin to another during epitaxy.

A Vac Sorp cryogenic pump is used to evacuate the growth tube, input gas lines, and hydrogen purifier to insure removal of both O_2 and H_2O from the system and to check the integrity of the system's joints and seals prior to each growth cycle. This pump system provides for the rapid exhausting of the system to less than 10^{-2} torr without risk of contamination due to backstreaming, a problem frequently encountered in systems employing oil based mechanical vacuum pumps.

The gas outlet line contains a high vacuum spring loaded check valve to provide a positive

system pressure during epitaxy and sealing of the
lines during the vacuum exhaust cycles. Initially
the valve was mounted directly onto the furnace
head but due to rapid failure caused by thermal
cycling and comtamination of the sealing ball
it was subsequently installed in the output line
about 12 inches downstream from the furnace head.
A Matheson #401X stainless steel valve which is
regularly disassembled and cleaned to provide
uncontaminated sealing surfaces is used for this
function.

b.   Epitaxial Boat Design

        All of the epitaxy conducted during this
program utilized multiple bin graphite epitaxial
boat which incorporated a sliding wafer holder
to transport the substrate wafer from one melt
to another during growth to achieve multiple
layered growth within a single thermal cycle.
A typical LPE boat used in this program is shown
in Figure 4. The basic boat consists of three
components, a four walled support frame, the
multiple bin melt container and the substrate
holder. In this design the bin assembly is placed
into the support frame where its base rests totally
on the sliding substrate holder. Direct broad
area contact is therefore maintained between the

Fig. 4. Multi-bin graphite LPE boat

bin assembly and slide at all times to assure
proper melt wiping during transport of the
substrate from one melt to another during growth.
In addition, this construction causes the
contacted surfaces which wear during repeated
processes to self compensate for the minor
deviations in mechanical tolerances which
naturally occur. In addition, the number of
melts or melt cross-section to be utilized
in any experiment can be economically varied
since a substitute or experimental bin assembly
can be easily inserted into the support frame
as required without replacement of or modification
to the remainder of the boat. In practice this
approach was used to modify the initial boats
from five bin to seven bin assemblies. Finally
the graphite plugs also shown in Figure 4 are
placed over the growth melts prior to epitaxy to
permit use of minimal melt charges while assuring
uniform distribution of the melts across the
substrate surface.

3.   Epitaxial Process and Results

A typical epitaxial growth sequence is
initiated by loading each boat melt bin with the
required (5 gm.) charge of 69 or 79 purity Gallium.
After loading the boat is inserted into the quartz
reactor tube which is then sealed and purged with
dry nitrogen. After purging the entire furnace system
including gas feed lines are evacuated to at least
10^{-2} torr to remove residual H_2O and O_2 and to
insure the integrity of the systems joints and seals.
Next high purity paladium diffused hydrogen is bled
into the system until its pressure releases the check
valve on the exhaust lines permiting normal gas flow
through the furnace system. At this point, the pre-
heated furnace chamber is rolled over the furnace
tube and the Gallium baked at 850°C for 20 minutes to
reduce the surface oxides which form on the Gallium
metal. After bake out the furnace chamber is rolled
back away from the growth tube and the melts and boat
permitted to slowly cool to ambient temperatures. After
cooling the system is once again flushed with dry
nitrogen and opened. The pre-weighed melt dopants
including sufficient Gallium Arsenide to saturate
the melts at the growth temperatures are then added
to the melts.   After inserting a freshly etched and
polished substrate wafer into the substrate holder the

boat is inserted into the tube, the tube sealed and
the furnace evacuation and purging process previously
described repeated. The furnace chamber is then
rolled over the growth tube and the boat heated to
850°C *to insure melt saturation.* Following the
saturation cycle, the furnace temperature control is
switched to the thermal program and the growth cycle
initiated. Using a quartz push rod in contact with
the sliding substrate holder the substrate wafer is
pushed under the first growth melt and growth
initiated at a stabilized cooling rate of 0.22°C per
minute. After the prescribed growth interval the
substrate holder is again pushed to slide the wafer
from the first melt to the second. This process is
repeated *for each melt to generate the required*
epitaxial structure. After growth of the final layer
the substrate is pushed clear of the boat to terminate
growth and wipe the residual gallium from its surface.
The furnace chamber is then removed from the furnace
tube, the tube cooled, nitrogen purged and opened.
After removal of boat from the furnace tube the
epitaxial wafer is cleaned in hot HCL, cross-sectioned,
etched to delineate the metalurgical interfaces and
inspected using a differential interference microscope
at 1000X. *Typical results of successful multi-layer*

epitaxy are shown in Figure 5 for a large optical cavity laser and in Figure 6 for a symmetrical optical cavity device. The specific details of epitaxial processes used to generate these structures which resulted in efficient multi-heterojunction GaAs lasers are shown in Table 2 and 3. During the development of the two processes just described numerous growth conditions and substrate preparation techniques were evaluated to improve the uniformity of the structures and repeatability of the growth process. It was found that the thickness and surface quality of the substrate were critical to epitaxial layer uniformity and flatness. Using a .016 inch recess in the slide to hold the substrate during epitaxy, best results are obtained with a substrate 0.014 inches thick. A thinner substrate results in layer non-uniformities due to melt carry over from one bin to the next during transfer of the seed wafer, while thicker substrates cause line growth defects in growth layers which are parallel to the sliding direction. This is primarily due to mechanical abrasion of the layer surface during the substrate transfer from one bin to the next. Surface defects or contamination generally result in non-uniform wetting of the substrate during the growth of the first GaAs or transition layer.

P-GaAs

P-GaAlAs t=2.0um

P-GaAs t<0.5um

N-GaAs t=1.7um

N-GaAlAs t=2.0um

N GaAs t=2.2um

N-GaAs Substrate

Figure 5. Cross section of epitaxial GaAs LOC laser structure used for the fabrication of GaAs LOC lasers.

P-GaAs

P-$(Ga_{1-y}Al_y)As$ t=1.9um

P-$(Ga_{1-x}Al_x)As$ t=2.5um

P-GaAs t<0.5um

N-$(Ga_{1-x}Al_x)As$ t=1.5um

N-$(Ga_{1-y}Al_y)As$ t=2.5um

N-GaAs t=1.8um

N-GaAs Substrate

Figure 6. Actual Cross-section of epitaxial wafer used for the fabrication of GaAs SOC lasers (1000X).

Page 22

TABLE 2

LPE Process for LOC Laser Fabrication

Ga gm.	GaAs mg.	Dopants mg.	Al mg.	Growth Time Minutes
5	400	15 Sn		15
5	425	15 Sn	3	15
5	450			3
5	450	10 Ge		.25
5	425	50 Ge	5	5
5	440	25 Ge		26

Initial Growth Time 845°C

Growth Rate 0.22°C/minute

TABLE 3

LPE Process for SOC Laser Fabrication

Melt Composition				Growth Time
Ga gm.	GaAs mg.	Dopants mg.	Al mg.	Minutes
5	400	10 Sn		17
5	400	10 Sn	7	18
5	435	5 Sn	1.2	4
5	450	15 Si, 10 Ge		.25
5	450	25 Ge	1.0	4
5	425	50 Ge	10	18
5	440	25 Ge		5

These growth defects are then propagated through all subsequent layers rendering the structure useless for device fabrication.

The effect of substrate meltback during growth of the transition layer on the uniformity of the total structure was also determined. Melt composition was adjusted to vary substrate meltback from 0 to about 0.002 inches. Best results were obtained for layers grown after an initial 0.001 inch substrate meltback. Excessive meltback again produced melt carry-over while insufficient or zero meltback caused a non-uniform. uneven first metallurgical interface that affected all subsequent layers.

Several methods of saturating the melts with GaAs at the growth temperature were also evaluated. Initially single crystal GaAs slugs which were shaped to bin cross-section were placed over the Gallium to both uniformity distribute the Gallium across the bin and provide source of Gallium Arsenide for melt saturation.

This approach was abandoned after several
growth attempts when it became evident that uniform
melt distribution across the bin base was not achieved
and the grown layers were highly irregular and contained
discontinuities. Improved results were obtained by
saturing the melts with weighed GaAs chunks and using
a graphite melt cover to distribute a thin($\simeq$.100 inch)
melt across the base of the bin.

Several methods were evaluated in attempts to
improve the surface quality of the last grown layer.
Ideally if all the Gallium could be removed from the
substrate surface after growth of the last layer but
prior to furnace cool down a final surface that could
be contacted directly for laser processing would result.
This would eliminate several processing steps as well
as positioning the junction closer to the heat sink
for improved thermal conduction during device operation.
Initially, all runs were pushed completely clear of the
last bin after growth and the tube removed from the
furnace chamber to permit rapid cooling to ambient.
However, this initial attempts were frustrated due to
lifting of the boat bin assembly during the sliding
motion which resulted in substantial melt carry over
and a large surface residue after the final wiping
action. The addition of two graphite screws which hold
the bin assembly against the slide during the growth

process eliminated this problem and permitted growth of final layers as thin as 2 microns with nearly Gallium free surfaces. Several attempts to fabricate lasers from these structures yielded only shorted devices. Examination of these failures indicated that the metalization process was incompatible with a 2 micron surface layer. Contact sintering as required by the existing process appeared to cause alloying beyond the depth of the junction thereby either shorting or damaging it. To eliminate this problem the substrate slice was permitted to remain under the last melt until the system cooled to ambient. This resulted in a final layer thickness of 50+ microns. Unfortunately these layers were characterized by both Gallium inclusions after about 25 microns growth,as well as an extremely poor surface due to Germanium growth on the surface during the final stages of cooling. A cross-section of one of these structures in shown in Figure 7.

Toward the end of the program several additional attempts were made to grow a top layer with a contactable surface without further processing. In these latter growths the top layer thickness was maintained at between 6 and 10 microns with removal of the substrate from the

Figure 7.   Cross-section of an epitaxial slice cooled
             in last bin to room temperature. Top layer
             is very thick with Ga inclusions and Ge on
             the surface. Run FR2-88   100X

Page 28

last melt used to terminate growth. Effective melt
wiping was achieved and the structures were contacted
without apparent detrimental effects to fabricated
devices. Other parameters which affected growth
quality included optimization of melt saturation
and development of process conditions and controls
which assured an oxygen free growth environment.
Examples of defects caused by improper melt saturation
or O_2 contamination of the growth environment are shown
in Figures 8 and 9. During the course of this work
over ninty epitaxial structures were generated. Of these
nearly 55% were of insufficient quality to justify
device fabrication. Many of the defective layers
resulted from process experimentation necessary to
develop an understanding of the furnace system and
the process sequence required for reproducible epitaxy.
Toward the second half of the program epitaxial
problems were largely resolved, therefore systematic
device optimization and evaluation using uniform
2.7cm^2 epitaxial wafers became feasible.

Figure 8.   Excess GaAs in last bin - damaged surface as wafer
was pushed out of last bin.   Run FR2-8 1000X.


Figure 9.   Non-uniform growth resulting from oxygen contamination
of growth ambient.   Run FR2-44   1000X.

C.   Device Results

The multi-heterojunction GaAlAs-GaAs epitaxial
structure grown during this program were continuously processed
into laser die which were then evaluated to determine the suit-
ability of the materials for laser fabrication. Initially
device results were quite eratic with most wafers containing
sufficiently large growth irregularities to render further
processing and evaluation unmeaningful. As experience was
gained in understanding the characteristics of the growth
furnace and epitaxial boat, epitaxial structure quality improved
making laser evaluation and characterization possible. Two
types of device structures were evaluated, the large optical
cavity laser and the symmetrical optical cavity device.
Most of the effort was directed to the former wafers which
yielded satisfactiry devices of each type. The growth
experience gained in LOC laser structure generation made
possible the rapid successful fabrication of SOC laser
structures. Performance results for both types of lasers
are shown in Figures 10 and 11. LOC lasers were fabricated
having optical cavities ranging from 1.5 to 40μm and re-
combination regions restricted to less of 0.5μm. The lasing
threshold currents for these devices ranged from 6KAcm^{-2} to
18KAcm^{-2} at 27°C. Differential quantum efficiencies up to
0.59 W/A were observed on non-reflective coated lasers and
up to 0.44 W/A on reflective coated devices. Emitted beam

GaAs LOC Laser

Chip size - 0.009 inch X 0.015 inch

$d < 0.5\mu m$
$d_C \approx 2.3\mu m$
$T = 27°C$
Pw= 75ns
PRR = 5KHz
λ = 894.5 nm

TYPICAL AOE= 49 W/A

BEST AOE= 60 W/A

$I_{TH} = 5.4$ KA cm^{-2}

$I_{TH} = 8.8$ KA cm^{-2}

FORWARD DRIVE CURRENT - AMPERES

Peak Emitted Power (Watts)

Figure 10. Performance characteristics of GaAs LOC laser.

GaAs SOC Laser

Chip Size - .009 inch x .016 inch

d_4 = < 0.5μm
d_c ≈ 3.2μm
d_3 = 1.5μm
d_5 = 1.2μm
T = 27°C
Pw = 75ns
PRR = 5kHz
λ = 899.8nm

Peak Emitted Power (Watts)

I_{TH}=14KAcm⁻² BEST AOE=64 W/A

I_{TH}=3.3KAcm⁻² TYPICAL AOE=53 W/A

Figure 11. Performance characteristics of GaAs SOC Laser.

patterns were highly dependent on optical cavity width. Typical results are shown in Figures 12 and 13. Best results were obtained for optical cavities of about 2.2μm. Devices having wider cavities were characterized by high order transverse optical modes which resulted in dispersed non-uniform far field emission patterns.

Far field emission patterns of the SOC lasers were generally more uniform than those of the LOC devices. Typical data taken during the course of structure optimization for the SOC devices are shown in Figures 14, 15 and 16 for the far field beam pattern perpendicular to the plane of the junction. Initially beams having 25 to 30 degrees full angle divergence at the 50% intensity points were consistently observed, however, by reducing the Aluminum content at the interior heterojunction beam divergence was reduced to about 18° degrees for devices fabricated near the end of the program. Additional reductions in beam divergence would be expected by reducing the Al concentration at the exterior heretojunctions which define the boundaries of the optical cavity. A second but no less important result of the reduced Al content at the interior heterojunction has been a marked increase in the threshold for catistrophic facet damage during laser operation. Initial SOC devices were damaged at emission intensities of about 0.5 watts per mil when driven with 60-75 nanosecond current pulses at 5 KHЗ. Recent devices exhibiting improved far field patterns have been operated at emission intensities up to 1.4 watts per mil at 60-75 nanoseconds and 15 KHЗ. Further improvements in this area could also be anticipated by continued structure optimization. A typical

Figure 12.   Emission pattern of DH LOC laser in plane perpendicular to laser junction.

BEAM SPREAD - DEGREES

Relative Radiant Intensity

Page 35

Figure 13. Emission pattern of DH LOC laser in plane parallel to laser junction.

Al Conc. bin 2 - .14%
Al Conc. bin 3 - .036%
Al Conc. bin 5 - .036%
Al Conc. bin 6 - .2%

BEAM SPREAD - DEGREES

Relative Radiant Intensity

Figure 14. Emission pattern of DH SOC laser in plane perpendicular to laser junction.

Page 37

Al Conc. bin 2 - .14%
Al Conc. bin 3 - .032%
Al Conc. bin 5 - .032%
Al Conc. bin 6 - .2%

BEAM SPREAD - DEGREES

Relative Radiant Intensity

Figure 15. Emission pattern of DH SOC laser in plane perpendicular to laser junction.

BEAM SPREAD - DEGREES

Relative Radiant Intensity

Al Conc. bin 2 - .14%
Al Conc. bin 3 - .024%
Al Conc. bin 5 - .02%
Al Conc. bin 6 - .2%

Figure 16. Emission pattern for DH SOC laser in plane perpendicular to laser junction.

Figure 17. Emission pattern of DH SOC laser in plane perpendicular to laser junction.

BEAM SPREAD - DEGREES

Relative Radiant Intensity

emission pattern for a SOC laser in the plane of the junction is shown in Figure 17.

All of the laser structures generated during this program utilized either Ge or Ge:Si as the P dopants. Typical 27°C emission wavelengths ranged from 886.0 to 899.5 nm for the Si:Ge doped material and from 883.5 to 885.5 for the Ge doped wafers. No evidence of Al carry-over from the Al doped melts to the GaAs melts was observed.

SECTION III

CONCLUSIONS

The primary task of the program namely the development of a liquid phase epitaxial growth environmental and process suitable for the reproducible growth of large area ($>2cm^2$), GaAlAs-GaAs multiple heterojunction structures suitable for the generation of efficient large optical cavity GaAs lasers has been achieved. A furnace system in which this epitaxy can be conducted has been demonstrated and suitable epitaxial processes for the growth of both LOC and SOC GaAs lasers developed. Many approaches to process optimization have been evaluated including methods of melt saturation, effect of surface substrate preparation, various growth rates and melt purification by vacuum or hydrogen firing on growth uniformity. Efficient LOC and SOC devices have been fabricated with the latter offering the potential of achieving all device performance goals including a high catistrophic failure level. In addition further structure and growth optimization for the SOC lasers also seem to offer continued reduction in emission pattern. Both LOC and SOC have achieved the desired threshold current density and efficiency at 27°C. However, SOC devices appear to posess lower lasing thresholds than comparable LOC devices offering the possibility of high peak power emission at low (20-30 KAcm^{-2}) drive current densities.

SECTION IV

REFERENCES

1.   H. F. Lockwood; H. Kressel; A. S. Sommers, Jr.;
         and F. Z. Hawrylo, "Applied Physics Letters"# 17,
         499 (1970).

2.   M. B. Panish; H. C. Casey, Jr.; S. Sumski and
         P. W. Foy; "Applied Physics Letters" # 22, 590
         (1973).

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY *(Corporate author)*	2a. REPORT SECURITY CLASSIFICATION
Laser Diode Laboratories, Inc. 205 Forrest Street Metuchen, New Jersey 08840	UNCLASSIFIED
	2b. GROUP

3. REPORT TITLE   Development of Large Area Multi-Layer Liquid Phase Epitaxy for Large Optical Cavity Laser Structures.

4. DESCRIPTIVE NOTES *(Type of report and inclusive dates)*

Final Technical Report

5. AUTHOR(S) *(First name, middle initial, last name)*

Robert B. Gill

6. REPORT DATE	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS
September 15, 1974		1

8a. CONTRACT OR GRANT NO	9a. ORIGINATOR'S REPORT NUMBER(S)
DAAK02-73-C0254	
b. PROJECT NO.	
	9b. OTHER REPORT NO(S) *(Any other numbers that may be assigned this report)*

DISTRIBUTION STATEMENT

11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY
	U. S. Army Night Vision Laboratory

13. ABSTRACT

The development of a liquid phase epitaxial process capable of yielding GaAlAs-GaAs multiple layer structures from which efficient lasers can be fabricated is discussed. The furnace facility is described in detail and the development of the LPE process is described. The application of various LPE processes to the growth of both large optical cavity and symmetrical optical cavity lasers is presented. Data is shown which depicts performance characteristics and emission patterns for the resultant devices.

DD FORM 1473 NOV 65

UNCLASSIFIED
Security Classification

14. KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Liquid Phase Epitaxy						
Gallium Arsenide Laser						
Injection Laser						
Heterojunction Laser						